



Properties & Gradations
STRUCTURAL MATERIAL APPLICATIONS

Certified test reports available

	3/4" (19mm)		1/2" (12.5mm)		3/8" (9.5mm)		Washed MS16 Fines (#4-0) (4.75mm-0)	
Typical Density (Unit Weight)	lbs/cf	kg/m ³	lbs/cf	kg/m ³	lbs/cf	kg/m ³	lbs/cf	kg/m ³
Dry Loose (ASTM C29)	48	768	50	800	52	832	60	960
Dry Rodded (ASTM C29)	55	880	56	896	58	928	65	1040
Saturated Surface Dry Loose (ASTM C29)	50	800	52	832	53	848	55	880
Maximum Dry Density (ASTM D4253)	60	960						
Damp Loose (ASTM C29)	48-52	768-832	50-54	800-864	51-55	816-880	53-57	848-912
Typical Relative Density (Specific Gravity)								
Dry (ASTM C127)	1.46		1.47		1.54		1.69	
Saturated Surface Dry (ASTM C127)	1.52		1.53		1.60		1.80	
Range in Saturated Surface Dry (ASTM C127)	1.47-1.54		1.49-1.55		1.57-1.64		1.75-1.85	
Sieve Size	% Passing		% Passing		% Passing		% Passing	
1" (25mm)	100		100		100		100	
3/4" (19mm)	90-100		100		100		100	
1/2" (12.5mm)			90-100		100		100	
3/8" (9.5mm)	10-50		40-80		80-100		100	
#4 (4.75mm)	0-15		0-20		5-40		85-100	
#8 (2.36mm)			0-10		0-20		N/A	
#16 (1.18mm)							40-80	
#30 (600µm)							N/A	
#50 (300µm)							5-35	
#100 (150µm)							5-25	