



STALITE Lightweight Aggregate
Physical Characteristics
STRUCTURAL FINES/MASONRY MATERIALS
Certified Test Reports Available

Absorption	Units	
Saturated Surface Dry	%	10-14
Soundness (% Loss)		
Freeze-Thaw	%	0.30-0.90
Impurities		
Clay Lumps	%	0-0.4
Organic Impurities	%	<1
Pop-outs	%	0
Aggregate Chemical Characteristics		
Ignition Loss	%	0-2
Stains		None