



Properties & Gradations
ROAD MATERIAL APPLICATIONS
Certified test reports available

	5/16"	5/16" (Washed)	5/16" (Special)	CA9	CA9 (Washed)	Tank D	Tank D (Washed)	MS16 (Washed)
	lbs/cf	lbs/cf	lbs/cf	lbs/cf	lbs/cf	lbs/cf	lbs/cf	lbs/cf
Damp Loose (ASTM C29)	53-57	53-57	53-57	53-57	53-57	53-57	53-57	53-57
kg/m ³	850-910	850-910	850-910	850-910	850-910	850-910	850-910	850-910
Sieve Size	% Passing	% Passing	% Passing	% Passing	% Passing	% Passing	% Passing	% Passing
#4 (4.75mm)	5-30	5-40	5-30	85-100	85-100	91-97	90-100	85-100
#8 (2.36mm)	0-10	0-20	0-10	10-40	10-40	59-75	50-70	N/A
#16 (1.18mm)	0-5	0-10	0-5	0-10	0-10	39-65	25-40	40-80
#30 (600µm)	N/A	N/A	N/A	N/A	N/A	23-38	10-25	N/A
#50 (300µm)	N/A	N/A	N/A	0-5	0-5	15-27	5-15	5-35
#100 (150µm)	N/A	N/A	N/A	N/A	N/A	9-19	0-5	5-25
#200 (75µm)	2.5 Max	0-2.5	N/A	N/A	N/A	N/A	0-3.0	N/A